



ASTEC® Re-Ply™ Roof System for SPRAYED POLYURETHANE FOAM (SPF) ROOFS®

*Application Specification # AC-2014-SPF
(15 Year Material & Labor Warranty)*

PART I - GENERAL

1.01 DESCRIPTION

- A. This guideline specification includes the installation of the fluid applied ASTEC® Re-Ply™ System. The process effectively repairs defects in the aged roof and renews the weathered surface to extend the useful life of the roofing system.
- B. Work included is labor, materials, equipment and accessories and related services to complete the application in accordance with guidelines and details as approved by ASTEC® Re-Ply™.
- C. This guideline does not specifically outline application procedures for preparation and finishing of roof drains, vents, ductwork, flashings, parapet walls or sheet metal work. This scope of work shall be submitted by the contractor prior to the commencement of work and shall be performed utilizing published trade related practices.

1.02 QUALITY ASSURANCE

- A. Manufacturer Qualifications: ASTEC® Re-Ply™ will furnish upon request, certification the material meets the physical properties stated in this guideline.
- B. Contractor Qualifications: All work to be completed must be done by an ASTEC® Re-Ply™ preferred applicator.
- C. No deviation from this guideline will be accepted without prior written approval of ASTEC® Re-Ply™.

1.03 SUBMITTALS

- A. All projects requiring ASTEC® Re-Ply™ System Turn Key Warranties must be submitted prior to commencement of work.
- B. Consult MSDS and Product Data Guideline for each product used before beginning work. MSDS and Product Specifications for each product are available at either www.icc-astec.com or from an ICC representative.

1.04 PRODUCT DELIVERY, STORAGE, AND HANDLING

- A. Containers are to be labeled with manufacturer's name, product name, description and identification.
- B. Deliver material in original, unopened packages and containers.
- C. Store materials in a dry area above 40° and protect from water and direct sunlight.
- D. Any materials damaged in handling or storage must **NOT** be used.

1.05 JOB CONDITIONS (CAUTIONS AND WARNINGS)

- A. All **NEW** mechanical equipment, vents, skylights, etc., should be in place before the roof restoration system is installed.
- B. Coatings should be protected from traffic and other abuse until completely cured and installation is complete.
- C. Application of coatings with spray equipment may require some masking and possible erection of wind screens to prevent over-spray and drift damage. Protect surfaces of unrelated areas from coatings and over-spray possibility.



1.05 Job Conditions cont.

- D. Application shall proceed **on** dry, clean surfaces only. In planning work consider environment and weather related conditions such as frost, mist, dew, condensation, humidity, and temperature. Temperature should be above 50° F. and rising, and stay above 40° F. long enough for initial cure to occur. Moisture should not be imminent.
- E. A wet surface or a surface that is not thoroughly cured can be very slippery. All work environments should comply with current OSHA regulations

1.06 WARRANTY

- A. ASTEC® Re-Ply™ Roofing Systems warrants that materials provided are free from defects in manufacturing and will replace any material found to be defective.
- B. All ASTEC® Re-Ply™ 15 Year Turn Key Warranty Systems must be installed by an authorized and trained contractor. Contact ASTEC® Re-Ply™ Representative or Technical Department for details regarding new and renewable warranty program.

PART 2 - PRODUCTS

2.01 GENERAL

- A. The components of the coating system are to be products of **ASTEC® Re-Ply™** or products approved as compatible and/or approved equal.
Physical Properties of Cured Roofing System: Testing of the coating system shall be done using guidelines under ASTM-D6083, “Standard Specification for Liquid Applied Acrylic Coating Used In Roofing”.

2.02 ASTEC® WPM # 9

- A. See Data Sheet

2.03 ASTEC® #2000 FINISH

- A. See Data Sheet

2.04 ASTEC® #4000 SURFACE CONDITIONER (REQUIRED IN CHALKY SURFACE CONDITIONS)

- A. See Data Sheet

2.05 REINFORCING FABRIC

- A. See Data Sheet

2.06 ASTEC® #2000 FLASH GRADE

- A. See Data Sheet

2.07 RELATED MATERIALS

- A. Caulks, adhesives, thinners, primers, flashing materials and products of a similar nature shall be approved by the manufacturer of the ASTEC® Re-Ply™ System prior to use. All accepted materials should be applied in accordance with its manufacturer’s specification and recommendations.

NOTE: See Product Data Guidelines for additional information and detailed instruction on each product.



PART 3 - APPLICATION

3.01 ROOF SUBSTRATE INSPECTION

- A. An acceptable substrate for the application of the ASTEC® Re-Ply™ System shall be provided.
- B. The roof surface must be clean, dry, and free of contaminants and structurally sound.
- C. Inspection shall include, but is not limited to, condition of flashings, drains, penetrations, skylights and other roof protrusions, as well as cracks and blisters.
- D. All insulated systems must be evaluated to assure materials are not wet. All wet insulation must be removed and replaced prior to installation of the Astec® Re-Ply™ System.
- E. The installed SPF system must conform to all requirements of the foam manufacturer.
- F. The installed SPF system must be a continuous unbroken system, completely covering the substrate being treated.
- G. The installed SPF system must be installed over only a sound, dry substrate. When a questionable substrate is involved, verification via a moisture analysis is required.
- H. The installer of the SPF system must provide all licenses, insurances, authorizations, and permits as required to complete the project as specified.
- I. The installer of the SPF system must conform to all safety requirements and regulations.

3.02 SURFACE PREPARATION & CLEANING

- A. Repair or replace damaged flashings, cracks and other imperfections. See 3.03 for details.
- B. Prepare the roof surface by removing loose debris and then high pressure washing with clean water to remove dirt and undefined soils, oily or greasy films and chalky residue.
- C. All blisters shall be cut, dried out & re-adhered or replacement membrane installed with approved & compatible mastic or approved ASTEC® Re-Ply™ product compliant with the existing substrate.
- D. After allowing repairs to thoroughly dry, apply the ASTEC® Re-Ply™ #2000 reinforced specification over repair areas.
- E. Allow repair areas to thoroughly dry before applying Astec® Re-Ply™ System as in 3.03

3.03 ASTEC® RE-PLY™ ROOF SYSTEM APPLICATIONS

- A. Flashing Systems-including all roof penetrations, protrusions & mechanical units. Apply ASTEC® #2000 Flash Grade in a uniform manner. While still wet, embed appropriate sized reinforcing fabric into wet ASTEC® #2000 Flash Grade. Apply a second coat of ASTEC® #2000 Flash Grade for a total coverage rate of 40 square feet per gallon resulting in a DFT of 30 mils. for odd or irregular shaped penetrations the use of WPM #10 is acceptable.
- B. Over the entire roof surface spray apply ASTEC® WPM 9 at a rate of 1.0 gallon per 100 square feet. While the sectioned area of ASTEC WPM 9 is still wet, embed sections of 36" wide x 360' long reinforcing fabric, making sure that the cloth is free of air bubbles, "fish mouths" and wrinkles. Cloth should overlap at areas where cutting is required.



3.03 ASTEC® Re-Ply® System Applications cont.

7. Spray apply second coat ASTEC® K DA over cloth, while the ASTEC® K DA is wet. Use of rollers or soft roof broom to back roll is required. Allow WPM # 9 to cure for 24 hours before applying Finish coat. Never leave reinforcing fabric uncoated overnight. Total for all coats of ASTEC® WPM # 9 shall be equal to 2.0 gallons per 100 square feet. Minimum coverage rate for total ASTEC® WPM # 9, not including reinforcing fabric, shall have an approximate DFT of 20 mils. Minimum coverage rate for total ASTEC® WPM # 9, including re-enforcing fabric, shall have an approximate DFT of 30 mils.
- D. Inspect surface area to be sure it is free of all moisture, dirt, dust and debris before applying the ASTEC® #2000 Finish.
- E. Apply ASTEC® #2000 Finish coat in two separate coats at a rate of 1.0 gallons per 100 square feet per coat using a cross-hatch pattern for the second coat. The ASTEC® Re-Ply™ Multi-layer system will result in a minimum of 4 gallons per 100 sq/ft, resulting in an approximate DFT of 50 mils over the reinforced roof area.

PROTECTION AND CLEAN-UP PROTECTION

- A. The roof system and all components must be protected from all other trades at the job site.
- B. All damage to the system must be repaired to comply with ASTEC® Re-Ply™ guidelines prior to final inspection for warranty approval. The cost of all related repairs will be the sole responsibility of the trades and/or subcontractors responsible for the damages.

CLEAN-UP

- A. Site cleanup is the responsibility of the contractor.
- B. All debris, containers, materials, equipment, and protection materials must be removed from the premises and properly disposed of. All work and storage areas must be in an undamaged and acceptable condition upon completion of clean up.

DETAIL WORK

- A. The purpose of this specification is to act as a guideline and is not intended to extensively describe preparation procedures, scope of work to drains, ductwork, skylights, flashings, parapets, copings, scuppers, etc. This work should be the result of consultation with contractors, manufacturer's representatives and end-users prior to commencement of the project and shall be performed using standard and acceptable trade practices.

NOTES

1. In lieu of the WPM #10, ASTEC® WPM # 9 can be applied and, while still wet, embed a layer of reinforcing fabric into the WPM # 9. Use caution to prevent voids and "fishmouths" in the fabric. Apply a top layer of ASTEC® WPM # 9 for a total coverage rate of 3 gallons of ASTEC® WPM # 9 per 100 square feet.
2. Renewable Warranty Process - follow guidelines for substrate inspection and surface preparation/cleaning found in section 3.01 & 3.02 that are applicable to the existing warranted system. Upon completion of the inspection and surface preparation follow guidelines found in "Coatings Application" Section 3.03 F. Consult your ICC Representative for additional information.
3. Foot Traffic- Areas of predictable excessive foot traffic, such as hatches, ladder access and around HVAC units should have a protective layer of reinforcing fabric and ASTEC® #2000 or compatible walk pads.



All materials in this document are, unless otherwise stated, the property of Insulating Coatings Corp. Copyright and other intellectual property laws protect these materials. © Copyright 2014

Contact information:

Insulating Coatings Corp. dba
ASTEC Re-Ply Roof Systems

Northern Office

27 Link Dr. Suite D
Binghamton, NY 13905
(800) 223-8494
(607) 723-1727

Southern Office

956 S. US Highway
Inverness, FL
(800) 345-5306
(352) 344-8741